

09/296,588

1. (Previously Presented) A reflective-type liquid crystal display comprising:
a first-type electrode;
a second-type electrode positioned opposite said first-type electrode and being of an opposite type than said first-type electrode; and
a liquid crystal material between said first-type electrode and said second-type electrode,
wherein at least one of said first-type electrode and said second-type electrode includes an amorphous carbon-containing layer adjacent said liquid crystal material, wherein said amorphous carbon-containing layer provides a level of conductivity corresponding to a resistivity between 10^4 and 10^{11} ohms-cm.
2. (Original) The reflective-type liquid crystal display in claim 1, wherein said first-type electrode comprises a transmissive-type electrode and said second-type electrode comprises a reflective-type electrode.
3. (Previously Presented) A reflective-type liquid crystal display comprising:
a first-type electrode;
a second-type electrode positioned opposite said first-type electrode and being of an opposite type than said first-type electrode; and
a liquid crystal material between said first-type electrode and said second-type electrode,
wherein at least one of said first-type electrode and said second-type electrode includes an amorphous carbon-containing layer adjacent said liquid crystal material, wherein said amorphous carbon-containing layer provides a level of conductivity corresponding to a resistivity between 10^4 and 10^{11} ohms-cm, and
wherein said amorphous carbon-containing layer comprises one of a hydrogenated amorphous carbon silicon, germanium, SiO_2 , Si_3N_4 and TiO_2 .
4. (Previously Presented) The reflective-type liquid crystal display in claim 1, wherein said amorphous carbon-containing layer has a unidirectional orientation matched to said liquid crystal material.

09/296,588

5. (Previously Presented) The reflective-type liquid crystal display in claim 1, further comprising one of a polyimide layer, polyamide layer and oblique-evaporated inorganic layer between said amorphous carbon-containing layer and said liquid crystal material.
6. (Original) The reflective-type liquid crystal display in claim 1, wherein a voltage between said first-type electrode and said reflective electrode varies a transparency of said liquid crystal material.
7. (Previously Presented) The reflective-type liquid crystal display in claim 1, wherein said amorphous carbon-containing layer comprises a passivation layer.
8. (Previously Presented) A reflective-type liquid crystal display comprising:
a transmissive electrode;
a reflective electrode positioned opposite said transmissive electrode; and
a liquid crystal material between said transmissive electrode and said reflective electrode,
wherein at least one of said transmissive electrode and said reflective electrode includes a diamond-like amorphous carbon layer adjacent said liquid crystal material, wherein said diamond-like amorphous carbon layer provides a level of conductivity corresponding to a resistivity between 10^4 and 10^{11} ohms-cm.
9. (Original) The reflective-type liquid crystal display in claim 8, wherein said transmissive electrode comprises indium tin oxide and said reflective-type electrode comprises aluminum.
10. (Previously Presented) A reflective-type liquid crystal display comprising:
a transmissive electrode;
a reflective electrode positioned opposite said transmissive electrode; and

09/296,588

a liquid crystal material between said transmissive electrode and said reflective electrode,

wherein at least one of said transmissive electrode and said reflective electrode includes a diamond-like amorphous carbon layer adjacent said liquid crystal material, wherein said diamond-like amorphous carbon layer provides a level of conductivity corresponding to a resistivity between 10^4 and 10^{11} ohms-cm, and

wherein said amorphous carbon layer comprises one of a hydrogenated amorphous carbon silicon, germanium, SiO_2 , Si_3N_4 and TiO_2 .

11. (Original) The reflective-type liquid crystal display in claim 8, wherein said amorphous carbon layer has a unidirectional orientation matched to said liquid crystal material.

12. (Original) The reflective-type liquid crystal display in claim 8, further comprising one of a polyimide layer, polyamide layer and oblique-evaporated inorganic layer between said amorphous carbon layer and said liquid crystal material.

13. (Original) The reflective-type liquid crystal display in claim 8, wherein a voltage between said transmissive electrode and said reflective electrode varies a transparency of said liquid crystal material.

14. (Original) The reflective-type liquid crystal display in claim 8, wherein said amorphous carbon layer comprises a passivation layer.

15. (Previously Presented) A method of forming a reflective-type liquid crystal display comprising:

forming a first-type electrode;

forming a second-type electrode positioned opposite said first-type electrode and being of an opposite type than said first-type electrode;

forming a liquid crystal material between said first-type electrode and said second-type electrode; and

09/296,588

forming an amorphous carbon-containing layer on at least one of said first-type electrode and said second-type electrode adjacent said liquid crystal material, wherein said amorphous carbon-containing layer is formed to provide a level of conductivity corresponding to a resistivity between 10^4 and 10^{11} ohms-cm.

16. (Original) The method in claim 15, wherein said forming of said first-type electrode comprises forming a transmissive-type electrode and said forming of said second-type electrode comprises forming a reflective-type electrode.

17. (Previously Presented) A method of forming a reflective-type liquid crystal display comprising:

forming a first-type electrode;

forming a second-type electrode positioned opposite said first-type electrode and being of an opposite type than said first-type electrode;

forming a liquid crystal material between said first-type electrode and said second-type electrode; and

forming an amorphous carbon-containing layer on at least one of said first-type electrode and said second-type electrode adjacent said liquid crystal material, wherein said amorphous carbon-containing layer is formed to provide a level of conductivity corresponding to a resistivity between 10^4 and 10^{11} ohms-cm, and

wherein said forming of said amorphous carbon-containing layer comprises forming one of a hydrogenated amorphous carbon silicon, germanium, SiO_2 , Si_3N_4 and TiO_2 layer.

18. (Previously Presented) The method in claim 15, wherein method includes forming said amorphous carbon-containing layer to have a unidirectional orientation matched to said liquid crystal material.

19. (Previously Presented) The method in claim 15, further comprising forming one of a polyimide layer, polyamide layer and oblique-evaporated inorganic layer between said amorphous carbon-containing layer and said liquid crystal material.

09/296,588

20. (Original) The method in claim 15, wherein a voltage between said first-type electrode and said reflective electrode varies a transparency of said liquid crystal material.